



CONNELLY – GPM, INC.

ESTABLISHED 1875

3154 SOUTH CALIFORNIA AVENUE CHICAGO, ILLINOIS 60608-5176
 PHONE: (773) 247-7231 • www.ConnellyGPM.com • FAX: (773) 247-7239

September 15, 2019



U.S. SCREEN NUMBER	OPENING	% PASSING
4	4.75 mm	100
8	2.36 mm	95 - 100
16	1.18 mm	75 - 90
30	0.600 mm	25 - 45
50	0.300 mm	0 - 10
100	0.150 mm	0 - 5

**MATERIAL WEIGHS
 APPROXIMATELY
 140 - 160 POUNDS
 PER CUBIC FOOT**

TYPICAL ANALYSIS OF IRON AGGREGATE

Iron/Iron Oxide	Balance
Total Carbon	2.48
Manganese	0.93
Sulphur	0.120
Phosphorous	ND
Silicon	0.35
Nickel	>0.01
Chromium	>0.01
Vanadium	ND
Molybdenum	0.33
Copper	0.10
Aluminum	>0.01
Magnesium	0.01
Boron	0.01
Zinc	0.01
Zirconium	0.01

**GALEN B. DIXON
 GENERAL MANAGER**